

1512 S BATAVIA AVENUE  
GENEVA, IL 60134  
630-232-0104

## Test Report

[www.riverbankacoustics.com](http://www.riverbankacoustics.com)

FOUNDED 1918 BY  
WALLACE CLEMENT SABINE

SPONSOR: **FabriTRAK Systems, Inc.**  
Mt. Laurel, NJ

**Sound Absorption**  
**RAL™-A23-301**

CONDUCTED: 2023-10-17

Page 1 of 9

ON: 2" TerraCORE® Poly Performance

### TEST METHODOLOGY

Riverbank Acoustical Laboratories™ is accredited by the U.S. Department of Commerce, National Institute of Standards and Technology (NIST) under the National Voluntary Laboratory Accreditation Program (NVLAP) as an ISO 17025:2017 Laboratory (NVLAP Lab Code: 100227-0) and for this test procedure. The test reported in this document conformed explicitly with ASTM C423-23: "Standard Test Method for Sound Absorption and Sound Absorption Coefficients by the Reverberation Room Method." The specimen mounting was performed according to ASTM E795-23: "Standard Practices for Mounting Test Specimens During Sound Absorption Tests." A description of the measurement procedure and room specifications are available upon request. The results presented in this report apply to the sample as received from the test sponsor.

### INFORMATION PROVIDED BY SPONSOR

The test specimen was designated by the sponsor as 2" TerraCORE® Poly Performance. The following nominal product information was provided by the sponsor prior to testing. The accuracy of such sponsor-provided information can affect the validity of the test results.

#### **Product Under Test**

---

Product Name: 2" TerraCORE® Poly Performance  
Material ID#: 6603  
Core Material: Polyethylene Terephthalate  
Core Nominal Thickness: 2"  
Core Nominal Density: 5.4 PCF  
Specimen Nominal Thickness: 2"  
Manufacturer: FabriTRAK Systems Inc.

1512 S BATAVIA AVENUE  
GENEVA, IL 60134  
630-232-0104

## Test Report

[www.riverbankacoustics.com](http://www.riverbankacoustics.com)

FOUNDED 1918 BY  
WALLACE CLEMENT SABINE

**FabriTRAK Systems, Inc.**  
2023-10-17

**RAL™-A23-301**  
Page 2 of 9

### SPECIMEN MEASUREMENTS & TEST CONDITIONS

Through a full external visual inspection performed on the test specimen, Riverbank personnel verified the following information:

#### Test Specimen

---

Dimensions: 8 @ 616 mm (24.25 in.) by 1219 mm (48 in.)  
2 @ 305 mm (12 in.) by 1219 mm (48 in.)  
Thickness: 50.14 mm (1.974 in.)  
Overall Weight: 23.36 kg (51.5 lbs)  
Mass per Unit Volume: 69.0 kg/m<sup>3</sup> (4.31 lbs/ft<sup>3</sup>)

#### Overall Specimen Properties

---

Size: 2.77 m (109.125 in) wide by 2.44 m (96.0 in) long  
Thickness: 0.05 m (1.974 in)  
Weight: 23.36 kg (51.5 lbs)  
Mass per Unit Area: 3.46 kg/m<sup>2</sup> (0.71 lbs/ft<sup>2</sup>)  
Calculation Area: 6.759 m<sup>2</sup> (72.75 ft<sup>2</sup>)

#### Test Environment

---

Room Volume: 291.98 m<sup>3</sup>  
Temperature: 19.5 °C ± 0.1 °C (Requirement: ≥ 10 °C and ≤ 5 °C change)  
Relative Humidity: 51.2 % ± 0.2 % (Requirement: ≥ 40 % and ≤ 5 % change)  
Barometric Pressure: 99.1 kPa (Requirement not defined)

### MOUNTING METHOD

Type A Mounting: The test specimen was laid directly against the test surface. Perimeter edges were sealed with metal framing and tape.

1512 S BATAVIA AVENUE  
GENEVA, IL 60134  
630-232-0104

## Test Report

[www.riverbankacoustics.com](http://www.riverbankacoustics.com)

FOUNDED 1918 BY  
WALLACE CLEMENT SABINE

**FabriTRAK Systems, Inc.**  
2023-10-17

**RAL™-A23-301**  
Page 3 of 9




Figure 1 – Specimen mounted in test chamber



Figure 2 – Individual specimen panel

1512 S BATAVIA AVENUE  
GENEVA, IL 60134  
630-232-0104

**Test Report**

[www.riverbankacoustics.com](http://www.riverbankacoustics.com)

FOUNDED 1918 BY  
WALLACE CLEMENT SABINE

**FabriTRAK Systems, Inc.**  
2023-10-17

**RAL™-A23-301**  
Page 4 of 9



Figure 3 – Detail of specimen material



1512 S BATAVIA AVENUE  
 GENEVA, IL 60134  
 630-232-0104

## Test Report

[www.riverbankacoustics.com](http://www.riverbankacoustics.com)

FOUNDED 1918 BY  
 WALLACE CLEMENT SABINE

**FabriTRAK Systems, Inc.**  
 2023-10-17

**RAL™-A23-301**  
 Page 5 of 9

### TEST RESULTS

Specimen total absorption and absorption coefficient are tabulated at the eighteen standard frequencies. A graphic presentation of the data and additional information appear on the following pages.

1/3 Octave Center Frequency (Hz)	Total Absorption (m <sup>2</sup> )	Total Absorption (Sabins)	Absorption Coefficient
100	1.42	15.25	0.21
** 125	2.45	26.34	0.36
160	2.61	28.06	0.39
200	3.65	39.26	0.54
** 250	4.45	47.85	0.66
315	5.75	61.89	0.85
400	6.71	72.25	0.99
** 500	7.33	78.90	1.08
630	7.66	82.43	1.13
800	7.82	84.13	1.16
** 1000	7.69	82.82	1.14
1250	7.57	81.53	1.12
1600	7.00	75.40	1.04
** 2000	6.95	74.83	1.03
2500	6.68	71.87	0.99
3150	6.44	69.29	0.95
** 4000	7.01	75.48	1.04
5000	7.17	77.18	1.06

**SAA = 0.98**  
**NRC = 1.00**

1512 S BATAVIA AVENUE  
GENEVA, IL 60134  
630-232-0104

## Test Report

[www.riverbankacoustics.com](http://www.riverbankacoustics.com)

FOUNDED 1918 BY  
WALLACE CLEMENT SABINE

**FabriTRAK Systems, Inc.**  
2023-10-17

**RAL™-A23-301**  
Page 6 of 9


### TEST RESULTS (continued)

The sound absorption average (SAA) is defined in ASTM C423-23 Section 3.1.1 as the arithmetic average of the sound absorption coefficients of a material for the twelve one-third octave bands from 200 Hz through 2500 Hz, inclusive, rounded to the nearest integer multiple of 0.01.

The noise reduction coefficient (NRC) is defined from previous versions of ASTM C423 as the arithmetic average of the sound absorption coefficients at 250 Hz, 500 Hz, 1000 Hz, and 2000 Hz, rounded to the nearest integer multiple of 0.05.

Tested by   
\_\_\_\_\_  
Marc Sciaky  
Senior Experimentalist

Report by   
\_\_\_\_\_  
Keith Kimberling  
Test Engineer

Approved by   
\_\_\_\_\_  
Eric P. Wolfram  
Laboratory Manager

1512 S BATAVIA AVENUE  
GENEVA, IL 60134  
630-232-0104

## Test Report


[www.riverbankacoustics.com](http://www.riverbankacoustics.com)

FOUNDED 1918 BY  
WALLACE CLEMENT SABINE

FabriTRAK Systems, Inc.  
2023-10-17

**RAL™-A23-301**  
Page 7 of 9

### SOUND ABSORPTION REPORT 2" TerraCORE® Poly Performance



**SAA = 0.98**

**NRC = 1.00**



RIVERBANK ACOUSTICAL LABORATORIES IS ACCREDITED BY NVLAP (LAB CODE 100227-0) FOR ACOUSTICAL TESTING SERVICES IN ACCORDANCE WITH ISO/IEC 17025:2017 AND FOR THIS PROCEDURE. THIS REPORT MUST NOT BE USED BY THE CLIENT TO CLAIM PRODUCT CERTIFICATION, APPROVAL, OR ENDORSEMENT BY RAL, NVLAP, NIST, OR ANY AGENCY OF THE U.S. GOVERNMENT. THIS REPORT SHALL NOT BE MODIFIED WITHOUT THE WRITTEN APPROVAL OF RAL. THE RESULTS REPORTED APPLY ONLY TO THE SPECIFIC SAMPLE SUBMITTED FOR TESTING; RAL ASSUMES NO RESPONSIBILITY FOR THE PERFORMANCE OF ANY OTHER SAMPLE.

1512 S BATAVIA AVENUE  
 GENEVA, IL 60134  
 630-232-0104

## Test Report

[www.riverbankacoustics.com](http://www.riverbankacoustics.com)

FOUNDED 1918 BY  
 WALLACE CLEMENT SABINE

**FabriTRAK Systems, Inc.**  
 2023-10-17

**RAL™-A23-301**  
 Page 8 of 9

### APPENDIX A: Extended Frequency Range Data

Specimen: 2" TerraCORE® Poly Performance (See Full Report)

*The following non-accredited data were obtained in accordance with ASTM C423-23, but extend beyond the defined frequency range of 100Hz to 5,000Hz. These unofficial results are representative of the RAL test environment only and intended for research & comparison purposes.*

1/3 Octave Band Center Frequency (Hz)	Total Absorption (Sabins)	Absorption Coefficient
31.5	6.85	0.09
40	3.21	0.04
50	7.71	0.11
63	7.54	0.10
80	7.24	0.10
100	15.25	0.21
125	26.34	0.36
160	28.06	0.39
200	39.26	0.54
250	47.85	0.66
315	61.89	0.85
400	72.25	0.99
500	78.90	1.08
630	82.43	1.13
800	84.13	1.16
1000	82.82	1.14
1250	81.53	1.12
1600	75.40	1.04
2000	74.83	1.03
2500	71.87	0.99
3150	69.29	0.95
4000	75.48	1.04
5000	77.18	1.06
6300	78.47	1.08
8000	76.51	1.05
10000	82.49	1.13
12500	77.87	1.07



RIVERBANK ACOUSTICAL LABORATORIES IS ACCREDITED BY NVLAP (LAB CODE 100227-0) FOR ACOUSTICAL TESTING SERVICES IN ACCORDANCE WITH ISO/IEC 17025:2017 AND FOR THIS PROCEDURE. THIS REPORT MUST NOT BE USED BY THE CLIENT TO CLAIM PRODUCT CERTIFICATION, APPROVAL, OR ENDORSEMENT BY RAL, NVLAP, NIST, OR ANY AGENCY OF THE U.S. GOVERNMENT. THIS REPORT SHALL NOT BE MODIFIED WITHOUT THE WRITTEN APPROVAL OF RAL. THE RESULTS REPORTED APPLY ONLY TO THE SPECIFIC SAMPLE SUBMITTED FOR TESTING; RAL ASSUMES NO RESPONSIBILITY FOR THE PERFORMANCE OF ANY OTHER SAMPLE.



1512 S BATAVIA AVENUE  
GENEVA, IL 60134  
630-232-0104

## Test Report

[www.riverbankacoustics.com](http://www.riverbankacoustics.com)

FOUNDED 1918 BY  
WALLACE CLEMENT SABINE

FabriTRAK Systems, Inc.  
2023-10-17

**RAL™-A23-301**  
Page 9 of 9

### APPENDIX B: Instruments of Traceability

Specimen: 2" TerraCORE® Poly Performance (See Full Report)

<u>Description</u>	<u>Model</u>	<u>Serial Number</u>	<u>Date of Certification</u>	<u>Calibration Due</u>
System 1	Type 3160-A-042	3160-106968	2023-07-17	2024-07-17
Bruel & Kjaer Mic And Preamp G	Type 4943-B-001	2525858	2023-05-03	2024-05-03
Bruel & Kjaer Pistonphone	Type 4228	2781248	2023-07-12	2024-07-12
EXTECH Hygro 639	SD700	A.103639	2022-12-07	2023-12-07

### APPENDIX C: Revisions to Original Test Report

Specimen: 2" TerraCORE® Poly Performance (See Full Report)

<u>Date</u>	<u>Revision</u>
2023-10-20	Original report issued
2023-11-14	All pages: added "®" to the sample designation per sponsor request. -EPW

---

END